

LOWER NICOLA COMMUNITY ARENA

AUGUST 2002

Problem: Concrete block wall acts as a heat sink allowing heat transfer

Solution: **SUPERTHERM**® RE19 Non-deteriorating Insulation (92%+ reflectivity)

Preparation : Waterblast concrete block wall substrate clean and dry



Masking east wall surrounding areas**First coat applied east wall @ 8 mils WFT**



Second coat west wall @ 8 mils WFT**First coat west wall @ 8 mils WFT**



Second coat applied @ 16 mils WFT total = 10 mils DFT finish 16 mils WFT total drying down to 10 mils DFT finish

